

June, 2015

3M™ Scotch-Weld™ Threadlocker Anaerobic Adhesive TL43

Product Description

3M™ Scotch-Weld™ Threadlocker Anaerobic Adhesives are one-component anaerobic adhesives that cure and seal threaded assemblies that meet a wide range of applications to prevent vibration loosening and/or leakage. All products provide excellent vibration, corrosion, and shock resistance. Engineered to provide different strengths, temperatures, nut/bolt sizes, and other requirements, some threadlockers allow removal and meet various selections depending on the specific application.

Product Features

- 3M™ Scotch-Weld™ Threadlocker TL43 is a general purpose. Removable with hand tools, medium strength threadlocker ideal for machine tool access bolts, and hydraulic system bolts. It can also be used on gear box / driveshaft bolts, bearing cover cap screws, countersunk screws, and conveyor roller bolts.
- Prevent corrosion
- Fluorescence
- Liquid (before cure)
- Shock and vibration resistance
- Fast setting
- 24 hour cure at room temperature



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Uncured Physical Properties

Property	Values	Notes
Color	Blue	
Chemistry	Dimethacrylate cP	
Viscosity	10,000-18,000 cP	Brookfield Viscometer spindle #3 at 2.5 rpm
Fixture Time	20min (avg time) (10-30min range)	Reference ISO 10964

Typical Mixed Physical Properties

Cure Speed:



Typical Cured Characteristics



Property	Values		Test Condition
Temperature Range	-54 to 149 °C	-65 to 300 °F	Constant
Color	Blue		Cured

Typical Performance Characteristics

Property	Values	Notes
Breakaway Torque	130in-lb - typical value (70-200in-lb range)	Reference ISO 10964. To convert to (N.m) divide (in.lb) by 8.851.
Prevailing Torque	60in-lb - typical value (20-200in-lb range)	Reference ISO 10964. To convert to (N.m) divide (in.lb) by 8.851.
Strength	Medium	

Typical Performance Characteristics (continued)

Hot Strength % Retention



3M™ Scotch-Weld™ Threadlocker Anaerobic Adhesive TL43

Handling/Application Information

Directions for Use

3MTM Scotch-Weld™ Threadlocker Anaerobic Adhesives are not recommended for use on most plastics due to potential cracking of plastic parts. Also, they are not recommended for use in piping systems that contain pure oxygen or an oxygen-rich environment, chlorine, or strong oxidizing substances.

For Assembly:

1. Ensure parts are clean, dry and free from oil, grease and dirt. For best results, clean and dry parts with solvent or 3MTM Scotch-Weld™ Activator. (Activator can also be used on inactive surfaces or to accelerate the cure on active surfaces.)
2. If not sure of surface type, always use activator. Refer to Material surface Activity and Cure Speed section for more information.
3. Shake the adhesive bottle well before use.
4. Avoid touching the metal surfaces with the bottle tip since the metal ions may react with the adhesive upon contact and eventually may clog the bottle tip.
5. Apply adhesive onto the threaded part where the contact area will be in the final assembly. For larger parts, use more adhesive and rotate the threaded part to spread adhesive evenly around contact area.
6. For through holes, apply several drops of adhesive onto the bolt at the nut engagement area. For blind holes, apply several drops of the adhesive down the internal threads to the bottom of the hole.
7. Assemble the nut / fastener and tighten as required.
8. Allow assemblies to set for sufficient time so that handling strength or full cure will occur before further processing or testing

For Disassembly:

1. Loosen or remove with regular hand tools.
2. If hand tools do not work due to the assembled parts being well tightened, apply localized heat (approx.. 400°F / 254°C) to the nut or bolt and disassemble while parts are still hot. Use extreme caution when working with heat sources (e.g. heat gun, flames, etc.)

Storage and Shelf Life

Store product in cool, dry area out of direct sunlight

3MTM Scotch-Weld™ Threadlocker Anaerobic Adhesives have a shelf life of 12 months when stored at 60° to 80°F (16° to 27°C) in the original unopened container.

Trademarks

3M and Scotch-Weld are trademarks of 3M Company.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~/3M-Scotch-Weld-Threadlocker-TL43?N=5002385+3293242477&rt=rud
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=TL43

Family Group

	TL22	TL42	TL43	TL62	TL70	TL71	TL72	TL77	TL90
Color Test Condition: Cured	Purple	Blue	Blue	Red	Green	Red	Red/Orange	Red	Green

ISO Statement

This product was manufactured under a quality system registered to ISO 9001 standards.

3M™ Scotch-Weld™ Threadlocker Anaerobic Adhesive TL43

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.



3M United States
3M Center
St. Paul, MN 55144-1000
800-362-3550
www.3M.com

Please recycle.
© 3M 2020. All Rights Reserved.

The brands listed above are trademarks of 3M